

## Low Density Conductive Polyurethane Foam CP5000L Series

### Typical Physical Properties

<u>Physical Property</u>	<u>Value</u>	<u>Test Method</u>
Color	Black	
Density (lbs / ft <sup>3</sup> )	1.7-1.9	ASTM D-3574-01
Indent Force Deflection@25%	45-55	ASTM D-3574-01
Surface Resistivity(Ohms/sq)	10 <sup>2</sup> - 10 <sup>4</sup>	ASTM D257
Ohms (point to point)	10 <sup>2</sup> - 10 <sup>4</sup>	
Volume Resistance(Ohm-CM)	10 <sup>2</sup> - 10 <sup>4</sup>	ASTM D257
Static Decay Time(in seconds)	.01 max	
Flame Resistance	NA	



<b>Part No.</b>	<b>Description</b>
CP5000L	24" x 36" x 1/4"
CP5001L	24" x 36" x 3/8"
CP5002L	24" x 36" x 1/2"
CP5003L	24" x 36" x 3/4"
CP5004L	24" x 36" x 1"

\* Custom Sizes & Designs Available

### Related Products:



This document is prepared for our customers as a service and is to the best of our knowledge true & accurate. However, it is understood & agreed by the users of this document that we will accept no liability for the conclusions reached. Users of this document may therefore wish to perform additional testing before determining that products mentioned are suitable.