

## Conductive Memory Foam PPF Series

<u>Physical Property</u>	<u>Value</u>	<u>Test Method</u>
Color	Black	
Density (lbs / ft3)	4.8-5.2	ASTM D-3574-01
Indent Force Deflection@25%	7-17	ASTM D-3574-01
Surface Resistivity(Ohms/sq)	$10^3 - 10^5$	ASTM D257
Ohms (point to point)	$10^3 - 10^5$	
Volume Resistance(Ohm-CM)	$10^3 - 10^5$	ASTM D257
Static Decay Time(in seconds)	.01 max	
Flame Resistance	NA	



<u>Part No.</u>	<u>Description</u>
PPF130	34" x 21" x 1/8"
PPF260	34" x 18 1/2" x 1/4"
PPF300	34" x 18 1/2" x .30"

### Related Products:



This document is prepared for our customers as a service and is to the best of our knowledge true & accurate. However, it is understood & agreed by the users of this document that we will accept no liability for the conclusions reached. Users of this document may therefore wish to perform additional testing before determining that products mentioned are suitable.