

Antistatic Stretch Wrap

Static Decay – FED STD 101C, Method

+5KV Less than 2 seconds

Surface Resistivity – $<10^{11}$ ohm/square nom

ASTM D 257

Tensile

Ultimate

Stretch Film

Yield

	mil	lbs	psi	%elong	lbs	psi	%elong
MD	0.78	7.1	9100	680		1.2	1570 62
TD	0.83	4.7	5680	1050		1.0	1200 18

Tear

MD	371 g Stretches & Oblique Tears
TD	585 g Stretches & Oblique Tears

Puncture – FED TEST 101C, Method 2065

	Mil	lbs/force	elong
Avg	0.85	4.1	2.4



Part No

Description

HW181500-80 17" x 1500', 80 GA, 4/CASE
 MW205000-80 20" x 5000', 80 GA

Related Products:

Antistatic Stretch Bundling Film:

SF08-3AS, 3" x 1,000', 18/CASE



This document is prepared for our customers as a service and is to the best of our knowledge true & accurate. However, it is understood & agreed by the users of this document that we will accept no liability for the conclusions reached. Users of this document may therefore wish to perform additional testing before determining that products mentioned are suitable.