

610 Presidential Dr, Suite 104 Richardson, Texas 75081

Marvelseal 1311B MIL-PRF-131K CLASS 3 MARVELSEAL 1311B COVALENCE COATED PRODUCTS RECOMMENDED SEAL CONDITIONS OT NO. H568 6-07 500F / 60PSI / 2 SEC Military Specification: MIL PRF 131K Type 1 Class 3 Physical Description: Laminated SCRIM, Foil and Polyethylene Application This film is a strong mil spec film that also has excellent moisture barrier properties. It is typically specified for large bags that must carry a heavy load. SCRIM, Foil, Poly conforms to FDA regulations Part 177.1520 CFR 21. Part No. Description Converting 36" x 200 yds MV1311B-36200 MV1311B-48200 48" x 200 yds It is usually converted into sheeting, tubing, 2-seal pouches and 3-seal pouches. **Physical Properties** Properties Test Method Unit of Measure **Typical Value MVTR** ASTM F1249 gms/100 sq. in./24hrs .0005 OTR ASTM D3985 cc/M sq. in./24 hrs .01 **TAPPI T403** 58 Burst psi **Tensile MD TAPPI T494** lbs. at break 20 **Tensile CD TAPPI T494** lbs. at break 20 **Related Products:**



This document is prepared for our customers as a service and is to the best of our knowledge true & accurate. However, it is understood & agreed by the users of this document that we will accept no liability for the conclusions reached. Users of this document may therefore wish to perform additional testing before determining that products mentioned are suitable.